

TECHNICAL DATA SHEET

Physical Properties	ASTM Testing Method	ULC S701 Standard	Type 1
Thermal Resistance 1 in. (25mm) hr·°F·ft ² /BTU (m ² ·°C/W)	C-518	Min: 3,7 Min: (0,65)	5,00* (0,88)
Water Vapour Permeability Perm. (ng/Pa·s·m ²)	E-96	Max: 5,3 Max: (300)	4,00 (226)
Dimensional Stability (%)	D-2126	Max: 1,5%	1,5%
Flexural Strength lb/in ² (kPa)	C-203	Min: 25 Min: (170)	25 (170)
Water Absorption (%)	D-2842	Max: 6,0%	1,1%
Compressive Properties lb/in ² (kPa)	D-1621	Min: 10 Min: (70)	10 (70)
*Thermal resistance based on 1 1/16 in. thickness according to the results displayed by BASF.			

ISO 9001:2015

Certified quality management system ISO 9001:2015



Warnock Hershey (WHI) certified according to **ULC S701** standard.

Polyform has been a leader in the plastics industry for over 50 years. The company has developed a great expertise in working with various raw materials. To learn more about technical data or other available materials, do not hesitate to contact your representative or our team at : sales@polyform.com.



POLYFORM
INDUSTRIAL

Polyform Cellular Plastics inc. | 454 Edouard Street, Granby, QC J2G 3Z3 | 1.800.463.8378
Phone: 450.378.9093 | Fax: 450.378.3096 | info@polyform.com | www.polyform.com